

DÉCOR STACKED STONE

PRODUCTS USED FOR LAYING STACKED STONE

KERABOND PLUS ADHESIVE (a powder to which Isolastic needs to be added)

- o 24hr drying period at 23°C
- o 14 days to cure
- o Clean tools with water and surface with a damp cloth

ISOLASTIC 50 (50% strength synthetic latex liquid)

- o Mix with Kerabond Plus adhesive for Stacked Stone heights under 2m
- o Helps deal with hot and cold temperature changes - movement and contraction; thermal exposure
- o Increases bond strength
- o New concrete should be cured for 6 months

ISOLASTIC PURE (a synthetic latex liquid)

- o Mix with Kerabond Plus adhesive for Stacked Stone heights 2m and over
- o Helps deal with hot and cold temperature changes - movement and contraction; thermal exposure
- o Higher bond strength
- o New concrete should be cured for 3 months

ALUMINIUM SUPPORT

- o An aluminium support must be fitted for all walls over 3m high.
- o Available from Décor Stone

MAPELASTIC SMART

- o Used as a heat barrier - for example a fire place surround
- o Cementitious Waterproof & Efflorescence barrier used to prime surfaces to which stacked stone is to be applied
- o Apply to a clean surface
- o Absorbent surfaces should be dampened first
- o Protect from water for 24 hours
- o Don't fill ponds for 5 days.
- o Remains flexible

DURA SLATE GLOSS SEALER

- o Solvent based sealer
- o Enhances the colour and gives a wet look

Please read product guide installation sheet before applying Stacked Stone

CONTACT DETAILS:

Décor Stone

84-90 Highbury Road Burwood VIC 3125

PH: (03) 9888 9888

F: (03) 9888 9884

W: www.decorstone.com.au

E: sales@decorstone.com.au